

METHOD AND PRODUCTS TO ABSORB OIL AND ORGANIC SOLVENTS  
FROM WATER AND FROM SEA

*12.6.1991*

The release of organic solvents and ~~of~~ oil into the environment and in water basins leads to disasters. <sup>ne</sup> And the consequences of these accidents are the destruction of the environment and the disruption of the chains of life.

10 A most critical such environmental problem is created by the release of oil during the sea transportation because of sea accidents. Another ~~such~~ critical problem directly connected with life is the pollution in sea ports and in enclosed seas around main cities.

15

Such pollution loads are also formed in navigable rivers and in lakes by ~~rejection~~ <sup>injection</sup> of petroleum and oil, and also during pumping of petroleum ~~in~~ rivers, ~~in~~ lakes and in sea from ~~the~~ existing ~~there~~ production wells <sup>where</sup> heavy pollution problems ~~are created~~.

The ~~facing~~ <sup>treating</sup> of those environmental problems is, up to date, unsuccessful, insufficient or incorrect. ~~detergents~~ are used with which the suspended petroleum and oils are emulsified to become bottom sludge deposits. ~~To the sea basin are thus summed huge pollution loads in between and in Mediterranean sea with intense petroleum~~ <sup>an</sup> transportation ~~transportation~~ traffic the pollution loading has become 0.3-0.8 g/liter and the bottom sludge formed exceeds the 2.000 tons/ km<sup>3</sup> which makes a World maximum.



The polymers bases in use are the following:

Polystyrene which after special processing becomes

~~macroplegmatic with Mc 50.000.~~

5

The trimeric copolymer SEBS (Styrene, Ethylene, Butadiene, Styrene) which is specially crosslinked to become <sup>macroreticular</sup> macroplegmatic.

10 ~~The elastomeric SBR fully hydrogenated with Styrene composition 10%, 20% and 40% which after special cross-linking and processing gave <sup>macroreticular</sup> macroplegmatic products of variation in absorbing capacities.~~

15 The cross-linking is advanced in solutions containing <sup>20-25% by weight of</sup> those polymers ~~20-25%~~ in chlorinated hydrocarbon solvents by ~~weight~~ such as dichloroethane with cross-linking agent ~~the 1,4-dichloromethyl-2,5-dimethylbenzene (DCMDMB) and~~ for catalytic action, ~~is used~~ tetrachlorotitan (TiCl<sub>4</sub>) <sup>is used</sup> in 10% solution in dichloroethane.

The appearance of thickness that is the cross-linking ~~result is related to the catalytic action which is added,~~ however, in small quantities in drops and is effective in high solution volumes.

In the following Tables are given the results of the <sup>weight ratio of</sup> cross-linking agent to the <sup>SEBS</sup> polymer ~~SEBS in weight ratio~~ in reaction at 60°C. To determine the absorption capacity, the porosity is studied, which was found to be low up to 4% of cross-linking agent and then <sup>increases</sup> to increase.

TABLE 1.

	DMDMB ,%	SEBS,resulted porosity (cm3/g )
5		
	1	0.294
	2	0.204
	4	0.279
	16	0.319
10	32	0.477

*The*  
~~It was then studied the~~ absorption capacity of organic  
 solvents selected from market products, derived from  
 petroleum, ~~was then studied~~

15

Table 2.

7 Absorption of Toluene in water- PS

	C initial PPM	C finalPPM
20	413,9	0.68
	102,1	0.59
	363,3	0.78

Absorption of Toluene Water-SEBS

25

410,4	0.4
319.6	0.39
119.9	0.37

30

Absorption of 1,2-Dichloroethane -  
Water , SEBS

	692,2	0.4
5	202,7	0.56

Absorption of Decane-water, SEBS

	456,2	0.35
10	623,4	0.37

Absorption of Petrol-water ,SEBS

	653,4	0.36
15	638,2	0.34

Table 3.  
Absorption capacity of the different absorption products  
per gram.

20		1	2	3	4
	PS	-	-	-	-
	SEBS	4,5	7,5	9.0	5,0
	SBR (10)	50,0	45.0	40.0	30.0
	SBR (20)	48.0	40.0	38.0	25.0
25		5	6	7	8
	PS	-	-	-	12
	SEBS	8	9.0	6.0	17
	SBR (10)	32.0	29.0	33.0	36
30	SBR (20)	27.0	26.0	31.0	31.0

	9	10	11	12	13
PS	17	28	25	18	18
SEBS	18	18	12	22	22
SBR (10)	37	-	-	16	15
5 SBR (20)	32	-	-	12	13

1 n-pentane, 2 n-hexane , 3 n-octane , 4 isooctane, 5 n-nonane, 6 n-decane 7 n-dodecane , 8 benzene, 9 toluene, 10 chloroform, 11 carbon tetrachloride, 12 1,2 dichloroethane, 13 1,1,3 trichloroethane .

The  
 with the above results which are successful and very  
 useful. <sup>we also</sup> ~~we have~~ studied the absorption capacity on oil  
 surface pollution in <sup>harbours</sup> ~~harbours~~ and the absorption capacity  
 15 in sea. For these trials, the absorption polymers were  
 placed in a polypropylene net in composition 20% PS, 30%  
 SEBS, 30% SBR (10) and 20% SBR (20), and the results  
 obtained were very impressive. <sup>It</sup> ~~And it~~ was proved that  
 the sweeping was not due to endomolecular absorption but  
 20 also due to external absorption adherence so that the  
 collection of oily matter was very satisfactory. <sup>The</sup> ~~That~~  
 load of <sup>oily</sup> ~~oil~~ matter is <sup>collected</sup> ~~brought~~ in a tank and is washed  
 with petroleum by which all those oils are collected as  
 useful fuels. That is this seeping action makes the  
 25 pollution loads useful and the harbours and the sea as  
 well as the sea bottom are liberated from oily and dirty  
 matter, and the ecology is overall improved.

# EXAMPLE 1

In a reactor of 0.5 m<sup>3</sup> capacity is brought (a)

~~1,2-dichloroethane 200 liter and is added (b) the polymer~~

5 SEBS, ~~20 kg.~~ <sup>100 gms</sup> and in the solution is added (c) 1,4-dichromethyl -2,5-dichlorobenzene ~~100 gms~~ and at 60°C is

added (d) the catalyst TiCl<sub>4</sub> as 10% solution. After agitation for 40 minutes the cross-linking started and

10 the solution becomes viscous and thick and cannot be agitated further. <sup>The product</sup> ~~Then~~ is taken off and is cut in a

mincing machine and then is brought to a reactor for taking the solvent out to become commercial product. <sup>The</sup> ~~That~~

reactor is heated up to 170°C under vacuum and stirring so that all the solvent is taken off and the polymeric

15 product is completely <sup>deodorized</sup> ~~deodorised~~.

~~Under the same conditions is treated the Polystyrene and -~~

the SBR 10%, 20% and 40% in Styrene fully hydrogenated to saturation with the addition of <sup>2%</sup> ~~the~~ crosslinking agent in

20 ~~as~~ in all, calculated on the benzene rings present.

# EXAMPLE 2

Products of example 1 in composition quantities

25 Polystyrene 30% , cross-linked SEBS 30% , cross-linked

SBR 10% in Styrene ,fully hydrogenated to saturation 20%

and SBR 20% in Styrene fully hydrogenated to saturation

20%, are brought <sup>in</sup> ~~on~~ a polypropylene net and are swept along on <sup>a</sup> ~~the~~ harbour surface. By sweeping the surface all

30 oily matter is collected in quantity 20% endomolecularly and in quantity 80% adhered externally. The net with the

loaded

polymers ~~loaded~~ is brought to a tank and washed with petroleum and the oily matter is recycled as fuel and the absorption polymers are ready to be <sup>reutilized</sup> ~~reutilised~~.

5

### EXAMPLE 3

Products of example 1 in composition quantities 10% crosslinked Polystyrene , 30% crosslinked SEBS , 40% crosslinked SBR , 10% in Styrene fully hydrogenated to saturation, are brought to sweep ~~the~~ sea surface pollution. The oil surface swept was that apart <sup>from</sup> ~~of~~ the main oxidised petroleum mass, which is collected otherwise. The materials of the net <sup>were drawn by boat to</sup> ~~swept~~ <sup>sweep</sup> successfully the sea surface ~~being drawn by a boat~~. All the oily water was collected and the sea net was brought to a tank <sup>Washing</sup> ~~washing~~ the net with petroleum <sup>reclaimed</sup> ~~to receive~~ the absorbed oily matter which was recycled as fuel, and the sea and the sea bottom pollution is avoided.

20

### EXAMPLE 4

In a lake where <sup>there</sup> is released petroleum and organic solvents from transportation and from production wells, ~~was brought~~ the net of example 3 ~~and~~ <sup>while</sup> is swept on the surface being drawn by a boat. The oily matter swept was by 25% endomolecularly absorbed and by 75% externally absorbed-adhered. It was <sup>collected</sup> ~~brought~~ in a tank and washed with petroleum to collect the oily matter absorbed as fuel and the net with the absorbing polymers was recycled <sup>for reuse</sup> ~~to use~~.

30



EXAMPLE 5

The polymer net of example 4 is placed at the flow of a  
5 river, the water of which contains oily matter. The  
action on the river was to collect all suspended oily  
matter, and the water flow is established with natural  
pure water flow.